



3M™ Polyester Label Material 7818EH

Product Data Sheet

June 2011
Supersedes : July 2009

Product Description

3M Polyester Label Material 7818EH is a 75 micron, silver polyester labelstock with a matt print receptive topcoat. This product utilizes 3M™ Adhesive 310E, a firm adhesive which resists oozing and provides high strength on a variety of surfaces including high surface energy (HSE) plastics and metals.

Product Descriptor / Dispatch Labelling

7818EH TT5 MS PET75-310E-90WG

Physical Properties

Not for specification purposes
(Calipers are nominal values)

Facestock	80 micron matt silver topcoated polyester
Adhesive	20 micron 310E acrylic
Liner	77 micron, 90 g/m ² White Densified Glassine

Key Features

- TT5 topcoat provides a smooth matt surface, enabling excellent thermal transfer images at reduced burn temperature settings. The topcoat also provides improved ink anchorage for traditional forms of press printing
- Good print definition is combined with the advantages of chemical and abrasion resistance associated with a matt coating.
- Polyester facestock provides durability in harsh environments.
- Adhesive provides high ultimate adhesion on a variety of substrates, and offers good chemical and UV resistance.
- Densified glassine liner for consistent die cutting.
- UL and cUL recognized (File Number MH18072)

Application Ideas

- Barcode labels and rating plates
- Property identification and asset labeling in harsh environments
- Warning, instruction, and service labels for durable goods.

Performance Characteristics

Not for specification purposes

Standard Test Conditions are 23°C and 50% Relative Humidity

180° Peel Adhesion tested using FINAT Test Procedure FTM 1 (300mm/min)
90° Peel Adhesion tested using FINAT Test Procedure FTM 2 (300mm/min)

Request [HERE](#) for more
information and/or quote.

See other 3M
self-adhesive mounts



Adhesion	20 Minutes at Standard Conditions		72 Hours at Standard Conditions	
	180° Peel N/25mm	90° Peel N/25mm	180° Peel N/25mm	90° Peel N/25mm
Stainless Steel	13.4	8.6	18.0	12.1
ABS	12.2	8.4	18.1	10.6
Polycarbonate	16.8	8.8	20.4	13.4
Polypropylene	8.6	3.8	11.1	5.2

Adhesion	72 Hours at 70°C		72 Hours at - 40°C	
	180° Peel N/25mm	90° Peel N/25mm	180° Peel N/25mm	90° Peel N/25mm
Stainless Steel	27.7	19.1	23.0	13.3
ABS	21.1	15.1	21.0	11.9
Polycarbonate	21.7	16.4	20.9	11.6
Polypropylene	5.9	4.2	11.4	6.6

Adhesion	72 Hours at 40°C and 95% RH	
	180° Peel N/25mm	90° Peel N/25mm
Stainless Steel	27.3	17.4
ABS	21.4	6.0
Polycarbonate	22.2	3.9
Polypropylene	10.9	4.1

Liner Release tested using FINAT Test Procedures
FTM 3 (180° removal of liner from face material at 300mm/min)
FTM 4 (180° removal of liner from face material at 10m/min)

Liner Release	Rate of Removal	Release Force	Units
FTM 3	300 mm per min	15.5	cN/50mm
FTM 4	10 m per min	5.7	cN/25mm

Temperature resistance of label applied to stainless steel.
Other substrates should be tested as per application

Service Temperature	-40 to 150°C
Minimum Application Temperature	5°C

Processing

Packaging:

Finished labels should be stored in plastic bags.

Printing:

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. Resin ribbons are recommended for optimum durability. It is printable by standard roll processing methods including flexography, hot stamp, letterpress, and screen printing

Die Cutting:

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

Request [HERE](#) for more information and/or quote.

See other 3M self-adhesive mounts



Special Considerations	<p>For maximum bond strength, the surface should be clean and dry. Isopropyl alcohol is a typical cleaning solvent.</p> <p>NOTE: When using solvents, read and follow the manufacturer's precautions and directions for use.</p> <p>For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 5°C can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.</p>
Storage	Store at standard room temperature conditions of 21°C and 50% relative humidity.
Shelf Life	At least 24 months from date of dispatch by 3M when stored in the original packaging at 21°C & 50 % relative humidity
For Additional Information	To request additional product information or to arrange for sales assistance, call 0870 6080050 Address correspondence to: 3M United Kingdom PLC, 3M House, 28 Great Jackson Street, Manchester, M15 4PA
Important Notice	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of 3M Company.

3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA	Product Information : Tel 0870 60 800 50 Fax 0870 60 700 99	3M Ireland Limited The Iveagh Building The Park, Carrickmines Dublin 18, Ireland	Customer Service : Tel (01) 280 3555 Fax (01) 280 3509
--	---	--	--



c/ Balançó i Boter, 22 Àtico. 08302 Mataró - Barcelona
T. +34 931 598 021 - M. +34 619 744 435
info@special-films.com | www.special-films.com

Request **HERE** for more
information and/or quote.

See other 3M
self-adhesive mounts